



Horizon 2020
Programme

SCREEN2

*This project has received funding from the European
Union's Horizon 2020 research and innovation programme
under grant agreement No 958211.*

Start date: 2020-11-01 Duration: 36 Months



FACTSHEET UPDATES **BASED ON THE EU FACTSHEETS 2020**

COKING COAL

AUTHOR(S):

TABLE OF CONTENT

Coking Coal.....	3
Overview.....	3
Market analysis, trade and prices.....	6
GLOBAL MARKET	6
3.2 EU TRADE	7
3.3. PRICE AND PRICE VOLATILITY	10
EU DEMAND.....	11
EU demand and Consumption	11
GLOBAL AND EU USES AND END-USES.....	12
substitution	14
4 Supply.....	15
EU supply chain	15
Supply from primary materials	17
Secondary production	22
Processing of coking coal	23
Other considerations	24
Health and safety issues related to the COKING COAL or specific/Relevant compouds at any stage of the life cycle.....	24
Environmental issues	24
Normative requirements related to Mining, use and processing of the COKING COAL.....	24
Socio-economic and ethical issues.....	25
Research and development Trends.....	26
References	27

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211

COKING COAL

OVERVIEW

Coking coal (or metallurgical coal) is a bituminous coal with a suitable quality that allows the production of metallurgical coke, or simply named coke. Coking coal has a higher carbon content than steam coal, as well as a lower level of sulphur, phosphorous and alkalis (World Coal Institute 2009). Coke is the main product of the high-temperature carbonisation of coking coal. Coke is an essential input material in steelmaking as it is used to produce pig iron in blast furnaces acting as the reducing agent of iron ore and as the support of the furnace charge. By-products of coke production such as tar, benzole, ammonia sulphate and sulphur are used for the manufacture of chemicals, as well a coke oven gas used for heat and power generation.




Figure 1. Simplified value chain for coking coal in the EU¹

Table 1. Coking coal supply and demand (extraction) in metric tonnes, 2016-2020 average

Global production	Global Producers	EU consumption	EU Share	EU Suppliers	Import reliance
778,633,768	China 52% Australia 18% Russia 9% US 6% India 5% Canada 3% Mongolia 2%	36,510,980	4.7%	Australia 28% Poland 26% US 20% Russia 8% Canada 6% Czech Republic 5%	65.6%

Prices: Coal prices started to sharply increase after 2003 due to the growing demand from emerging economies (EC, 2020). In particular, the strong demand for steel from China due to large infrastructure projects supported and continues to support high prices for coking coal (EC, 2020). In 2021, coal prices increased significantly, with European prices averaging \$121/tonne and the Asian market price averaging \$145/t, its highest since 2008 (BP, 2022).

¹ JRC elaboration on multiple sources (see next sections)

This project has received funding from the European Union's Horizon 2020 research and innovation programme under grant agreement No 958211

Primary supply: The global production of coking coal decreased by 3.2% in 2020. Contrary to the others producers, China increased production by 2.8%, (+ 15 Mt). Production in the United States decreased by the same tonnage, representing a cut of 23%. Production in Australia and the Russian Federation also decreased, by 2.8% and 6.8% respectively (iea.org, 2022). The annual average production of coking coal in EU during the period 2016-2020 was about 15 Mt. Poland is the major producer with an average annual production 13 Mt. Smaller amounts are extracted in Germany and Czech Republic. The extraction in Germany was interrupted after 2018. About 39 Mt of coking coal were annually imported during 2016-2020. The most important trade partners are: United states (9.7 Mt) Australia (5.6 Mt) Canada (1.9 Mt) Russia (2.4 Mt).

Secondary supply: there is no secondary supply of coking coal.




Figure 2. Annual average price of coking coal between 2000 and 2020 (USGS, 2021)².




Figure 3. EU sourcing of coking coal and global mine production (update)

² Values in €/kg are converted from original data in US\$/kg by using the annual average Euro foreign exchange reference rates from the European Central Bank (https://www.ecb.europa.eu/stats/policy_and_exchange_rates/euro_reference_exchange_rates/html/eurofxref-graph-usd.en.html)

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211

Uses: Steel production accounts for most of the coking coal consumption in the EU (82%), with other end use applications including heat & electricity.




Figure 4: EU uses of RM

Substitution: There are no technologically feasible and economically reasonable alternatives to completely replace coking coal at scale in the production of steel from iron ore (Eurofer 2019b). Coking coal (coke) can be replaced by pulverised coal (PCI) up to a certain level, which then requires the remaining hard coking coal to be of higher quality, mainly premium hard coking coal, otherwise the performance of steel production process can be strongly lowered (Eurofer 2019b). Hydrogen and natural gas potentially used in the blast furnace are not substitutes of coking coal *per se* as they do not provide mechanical support to the charge of the blast furnace nor the necessary carbon monoxide (CO) for reducing the iron ore but perform only the function of delivering heat (CRM experts 2019).

Table 2. Uses and possible substitutes

Use	Percentage*	Substitute	Comment on substitute
Coke for steel production	82%	<ol style="list-style-type: none"> Other type of coke Natural gas Pulverised coal (PCI) Waste plastics Hydrogen 	<ol style="list-style-type: none"> Similar or lower costs; reduced performance. Higher costs (up to 2X). Similar performance. Similar or lower costs; reduced performance Similar or lower costs; reduced performance Very high costs (more than 2x); similar performance.
Coke for other applications	30%	Not assessed – under 10%.	
Other	10%	Not assessed – under 10%.	

* EU end use consumption share.

Other issues: Coking coal is produced in coke ovens, and the coking coal is used in the aluminium, steel, graphite, electrical, and construction industries. Chronic (long-term) exposure to emissions from coke ovens and from the aforementioned industries results in conjunctivitis, severe dermatitis, lesions of the respiratory system and digestive system. Epidemiologic studies of coke oven workers have reported an increase in cancer of the lung, trachea, bronchus, kidney, prostate, and other sites. Animal studies have reported tumours of the lung and skin from inhalation exposure to coal tar. EPA (Environmental Protection Agency) has classified coke oven emissions as a Group A, known human carcinogen. (IRIS 2022).

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211

MARKET ANALYSIS, TRADE AND PRICES

GLOBAL MARKET

Table 3: Coking coal (extraction) supply and demand in metric tonnes, 2016-2020 average

Global production	Global Producers	EU consumption	EU Share	EU Suppliers	Import reliance
778,633,768	China 52% Australia 18% Russia 9% US 6% India 5% Canada 3% Mongolia 2%	36,510,980	4.7%	Australia 28% Poland 26% US 20% Russia 8% Canada 6% Czech Republic 5%	65.6%

Table 4: Coking coal (processing) supply and demand in metric tonnes, 2016-2020 average

Global production	Global Producers	EU consumption	EU Share	EU Suppliers	Import reliance
628,454,400	China 71% Russia 7% Japan 5% India 4% South Korea 3%	22,684,264	3.6%	Germany 41% Poland 41% France 3% Czech Republic 2% Italy 2% Netherlands 2% Russia 2% Slovakia 2%	0%

Coking coal trade reflects the demand for iron ore, pig iron and crude steel (EC, 2020). There has been a substantial increase in coking coal consumption during the last 40 years, driven primarily by growing steel production in China as infrastructure has been expanded (IEA 2021). In 2020, China accounted for 53% of global coal demand, and together with India (12%) represented almost two-thirds of global coal demand (IEA, 2021). Coking coal is traded both through contracts and in the spot market (EC, 2020). Coal spot prices can fluctuate based on short-term market conditions, but contract prices tend to be more stable (EIA, 2021).

Despite the trend in the last decades, the production of hard coal decreased 4.5% in 2020 compared with 2019 as a result of the COVID-19 disruptions. Furthermore, total coal consumption declined 4.4% in 2020 compared with 2019, and the coal use for power production dropped 4.2% as a result of lower electricity consumption, growth in renewable generation, and low gas prices (Eurocoal, 2021). However, such trends were very specific depending on the region. For instance, the EU coal demand went down by 22%, while Chinese coal demand (and supply) did not change significantly between 2019 and 2020 (Eurocoal, 2021). It is expected a rebound in global coal demand in 2021, in which demand will rise by 4% compared with the 2019 demand, which also includes potential reductions in coal use as result of the energy transition initiatives, especially in the US and EU (EIA, 2021).

This project has received funding from the European Union's Horizon 2020 research and innovation programme under grant agreement No 958211

3.2 EU TRADE

For this assessment, coking coal is evaluated at both extraction and processing stage.

Table 5. Relevant Eurostat CN trade codes for coking coal

Mining		Processing/refining	
CN trade code	title	CN trade code	title
27011210	Coking coal, whether or not pulverised, but not agglomerated ³	27040010 ⁴	Coke and semi-coke of coal, whether or not agglomerated
		27040011	Coke and semi-coke of coal, whether or not agglomerated, for the manufacture of electrodes
		27040019	Coke and semi-coke of coal, whether or not agglomerated (excl. for the manufacture of electrodes)

As shown in Figure 1, the EU has historically been a net importer of coking coal. The EU consumption is driven by the demand from the steel (European Commission, 2020). In the past 9 years (2010-2019), the EU import has remained relatively stable at 32,000,000 tonnes/year. In 2020, with the steel production cuts and lockdowns during the COVID-19 pandemic (Fastmarkets, 2021), the EU import of coking coal reached the lowest level since 2000 at 20,550,052 tonnes. In 2021, the situation slightly recovered with an increase up to 28,826,366 tonnes, worth approximately 4.4 billion Euro (Georgitzikis, K., D`elia, E. and Eynard, U., 2022). The EU imports represented about two thirds of the total EU sourcing in 2021 (Georgitzikis, K., D`elia, E. and Eynard, U., 2022). The EU export has remained relatively unchanged since 2000. In 2021, the EU export of coking coal was 45,771 tonnes. Most of the coking coal imported to the EU originates from Australia and the USA (Figure 2). Russia and Canada have always been among the EU exporters of coking coal as well, with total average 2000-2021 share of 19%. The import volume from Russia peaked at 5.6 Mt in 2018 (or 16% of extra-EU coking coal imports), but coking coal imports from Russia declined substantially in 2019 (Georgitzikis, K., D`elia, E. and Eynard, U., 2022).

³ Coking coal belongs to Metallurgical coal family; coal that comprises coking coal of various qualities (hard, semi-hard and semi-soft) and coal for Pulverised Coal Injection (PCI)

⁴ Since 2013, substituting CN 27040011 'Coke and semi-coke of coal, whether or not agglomerated, for the manufacture of electrodes' and 27040019 Coke and semi-coke of coal, whether or not agglomerated (excl. for the manufacture of electrodes).




Figure 5. EU trade flows of Coking coal, whether or not pulverised, but not agglomerated (CN 27011210) from 2000 to 2021 (Eurostat, 2022)




Figure 6. EU imports of Coking coal, whether or not pulverised, but not agglomerated (CN 27011210) by country from 2000 to 2021 (Eurostat, 2022)

Until 2013, coke and semi-coke of coal whether or not agglomerated were reported under two CN codes: 27040019 (Coke and semi-coke of coal, whether or not agglomerated, for the manufacture of electrodes) and 27040011 (Coke and semi-coke of coal, whether or not agglomerated (excl. for the manufacture of electrodes)). From 2014 both are reported under the CN code 27040010 (Coke and semi-coke of coal, whether or not agglomerated).

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211

Globally, imports of coke and semi-coke of coal have declined from 10 million tonnes in 2003 to 2 million tonnes in 2009, to the level lower than the exports (See Figure 7).




Figure 7. EU trade flows of Coke and semi-coke of coal, whether or not agglomerated (CN 27040019 + CN 27040011 until 2013 and CN 27040010 from 2014) from 2000 to 2021 (Eurostat, 2022)

Before 2009, the majority of supplies of this product to the EU originated from China first and then Russia, Australia and Ukraine. The supply from China has significantly declined from 2000-2008 (Figure 8).

After 2009, the main suppliers to the EU have been Russia first and then China, UK and Canada and a lower extent. The EU export stayed at the order of 2,8 million tonnes while the imports at 1,5 million tonnes in 2021.

Similar to the EU imports of coking coal, the year 2020 saw a decrease in import quantity of coke and semi-coke of coal following the impact of the Covid-19 pandemic on steel production and recovery in 2021.

In addition, approximately 30% of European consumption of Pulverised Coal Injection (PCI) coal originates from Russia. Russia supplies Europe with almost all of its low-sulphur PCI coal (Georgitzikis, K., D`elia, E. and Eynard, U., 2022). However, specific trade data for PCI coal in international statistics are not available (Georgitzikis, K., D`elia, E. and Eynard, U., 2022).

The risk of supply disruption due to the Russo-Ukrainian war is rising due to the current tight market balance globally, which is projected to last at least until 2024 (Georgitzikis, K., D`elia, E. and Eynard, U., 2022). On 8 April 2022, the EU approved an import ban on all forms of Russian coal, worth EUR 8.2 billion in 2021, as part of the fifth wave of sanctions against Russia in response to Ukraine’s invasion. The ban, which has been fully effective from the second week of August 2022, includes imports of coking coal and coke, worth EUR 550 million in 2021 or about 7% of the total value of banned coal imports from Russia (Georgitzikis, K., D`elia, E. and Eynard, U., 2022).




Figure 8. EU imports of Coke and semi-coke of coal, whether or agglomerated (CN 27040019 + CN 27040011 until 2013 and CN 27040010 from 2014) by country from 2000 to 2021 (Eurostat, 2022)

3.3. PRICE AND PRICE VOLATILITY




Figure 9. Annual average price of coal between 2000 and 2021, in US\$/t and €/t based Northwest Europe marker price⁵. Dash lines indicate average price for 2000-2021 (BP, 2022)

⁵ Values in €/kg are converted from original data in US\$/kg by using the annual average Euro foreign exchange reference rates from the European Central Bank

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211

Coal prices started to sharply increase after 2003 due to the growing demand from emerging economies (EC, 2020). In particular, the strong demand for steel from China due to large infrastructure projects supported and continues to support high prices for coking coal (EC, 2020).

In 2021, coal prices increased significantly, with European prices averaging \$121/tonne and the Asian market price averaging \$145/t, its highest since 2008 (BP, 2022).

EU DEMAND

EU DEMAND AND CONSUMPTION

It should be noted that the aforementioned consumption levels of coking coal and coke include the use of PCI in the blast furnace (see Section 8.3.3), and PCI injection has already reached its technical limits in the EU industry (Eurofer 2019a).

Coking coal extraction stage EU consumption is presented by HS code CN 27011210 “Coking Coal, whether or not pulverised, but not agglomerated”. Import and export data is extracted from Eurostat Comext (2022). Production data is extracted from WMD (2022).




Figure 10. Coking coal (CN 27011210) extraction stage apparent EU consumption. Production data is available from WMD (2022). Consumption is calculated in coking coal content (EU production+import-export).

Coking coal processing stage EU consumption is presented by HS codes CN 27040010 ‘Coke and semi-coke of coal, whether or not agglomerated’, CN 27040011 ‘Coke and semi-coke of coal, whether or not agglomerated, for the manufacture of electrodes’ and CN 27040019 ‘Coke and semi-coke of coal, whether or not agglomerated. Import and export data is extracted from Eurostat Comext (2022). Production data is extracted from VDKI (2020).

(https://www.ecb.europa.eu/stats/policy_and_exchange_rates/euro_reference_exchange_rates/html/eurofxref-graph-usd.en.html)

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211




Figure 11. Coking coal (CN 27040010, CN 27040011 and CN 27040019) processing stage apparent EU consumption. Production data is available from VDKI for 2003-2018. Consumption is calculated in coking coal content (EU production+import-export).

Based on Eurostat Comext (2022), WMD (2022) and VDKI (2020) average import reliance of coking coal at extraction stage is 65.6 % for 2016-2020 and average import reliance of coking coal at processing stage (coke) is 0 % for 2014-2018.

GLOBAL AND EU USES AND END-USES

Steel production accounts for most of the coking coal consumption in the EU, with other end use applications including heat & electricity.




Figure 12: EU end uses of coking coal (average 2013-2017 No further data available) (IChPW 2019) and EU consumption of coking coal and coke (average 2016-2020 for coking coal and 2014-2018 for coke) (Eurostat Comext 2022; WMD 2022; EC Data 2023)

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211

Relevant industry sectors are described using the NACE sector codes (Eurostat 2019). The calculation of economic importance is based on the use of the NACE 2-digit codes and the value added at factor cost for the identified sectors (Table 1). The value-added data correspond to average 2012-2016 figures.

Table 6. Coking coal applications, 2-digit and examples of associated 4-digit NACE sectors, and value-added per sector (IChPW 2019) (SCRREEN workshops 2019) (Eurostat 2019).

Applications	2-digit NACE sector	Value-added of sector (millions €)	Examples of 4-digit NACE sector
Coke for steel production	C24 – Manufacture of basic metals	63,700	C24.10 - Manufacture of basic iron and steel and of ferro-alloys
Coke for other application	C23 – Manufacture of other non-metallic mineral products	72,396	C2399 – Manufacture of other non-metallic mineral products n.e.c
Other uses (tar, benzole, electricity and heat)	C20 – Manufacture of chemicals and chemical products	117,150	C20.14 – Manufacture of other organic basic chemicals –Distillation of coal tar C20.15 – Manufacture of fertilizers and nitrogen compounds ammonia




Figure 13. Coking coal applications, 2-digit and associated 4-digit NACE sectors, and value added per sector (Eurostat, 2019b))

STEEL PRODUCTION

- The steel making process is the most significant application of coking coal.
- 90% is used in the iron making process (blast furnace) for generating process heat, also as a reduction medium of iron ores; carburisation of the hot meta; supporting the furnace charge; and providing permeability inside the furnace.
- More than 70% of world steel production is made by the integrated steelmaking route which is based on the blast furnace (BF) and basic oxygen furnace (BOF) processes, and relies on coking coal (World Coal Association 2019) (World Coal Institute 2009).

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211

- 60% of steel production in the EU (which requires coking coal) is produced via the blast furnace route (European Commission 2018).
- The average production of one tonne of steel in the integrated steelmaking process requires the use of 630 kilograms of coke, and therefore 780 kilograms of coking coal (WorldSteel 2019a) (World Coal Institute 2009).
- As the energy transition movement is gaining momentum, it is expected that steel production will reduce its dependence on coking coal and focus on alternatives such as green hydrogen.

OTHER APPLICATIONS:

- 1% of coking coal is used in the manufacture of electrodes generally intended for the metallurgical industry, and tar is an essential source material (BIO Intelligence Service 2015)
- Coking coal is also used in the production of foundry coke employed in foundry melting furnaces by some producers of base metals and ferroalloys (FeMn and FeCr).
- Other minor users of metallurgical coke include producers of non-metallic minerals such as phosphates, calcium carbide, soda ash and stone wool, or as household heating.

TAR, BENZOYL, ELECTRICITY & HEAT:

- Several products can be produced from by-products (coke oven gas, benzole, coal tar, ammonia sulphate and sulphur) of coke ovens.
- Ammonia gas recovered from coke ovens is used to manufacture ammonia salts, nitric acid and agricultural fertilisers, while refined coal tar is employed in the manufacture of chemicals (e.g. creosote oil, naphthalene, phenol, and benzene) as well as in carbon fibres (World Coal Association 2019) (Remus et al. 2013) (Ozon 2018) (Diez, Alvarez, and Barriocanal 2002) (JSW 2019a).
- Benzole (benzene, toluene, xylene) is also used in the chemical industry, whereas coke oven gas can be used for heat and power generation as it contains almost 55% of hydrogen (IChPW 2019).

SUBSTITUTION

Substitutes have been identified for the applications of coking coal.

Table 7: Substitution options for coking coal by application (SCRREEN Validation Workshop, 2022; EC Data 2023 files). USGS 2022.

Use	Percentage*	Substitute	Comment on substitute
Coke for steel production	82%	6. Other type of coke 7. Natural gas 8. Pulverised coal (PCI) 9. Waste plastics 10. Hydrogen	6. Similar or lower costs; reduced performance. 7. Higher costs (up to 2X). Similar performance. 8. Similar or lower costs; reduced performance 9. Similar or lower costs; reduced performance 10. Very high costs (more than 2x); similar performance.
Coke for other applications	30%	Not assessed – under 10%.	
Other	10%	Not assessed – under 10%.	

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211

* EU end use consumption share.

COKE FOR STEEL PRODUCTION

- There are no technologically feasible and economically reasonable alternatives to completely replace coking coal at scale in the production of steel from iron ore (Eurofer 2019b).
- Coking coal (coke) can be replaced by pulverised coal (PCI) up to a certain level, which then requires the remaining hard coking coal to be of higher quality, mainly premium hard coking coal, otherwise the performance of steel production process can be strongly lowered (Eurofer 2019b).
 - Pulverised coal injection is a technique widely applied in the EU (Addendum in Pardo, Moya and Vatopoulos, 2015), and the industry has already reached the technical limits for coke substitution (Eurofer 2019a). For this reason, PCI does not affect the substitution index of coking coal in the criticality assessment. A 30% substitution of coking coal with PCI was assumed in the EU MSA study of coking coal (background data from (BIO Intelligence Service 2015)).
 - Ca. 30% of coal can be saved by injecting fine coal particles into the blast furnace as one tonne of PCI coal used for steel production can replace about 1.4 tonnes of coking coal by reducing the amount of coke required.
 - Coals used for pulverised coal injection into blast furnaces have more narrowly defined qualities than steam coal (WorldSteel 2019a).
 - PCI coal is mainly used to achieve cost benefits by replacing coke, thus skipping the costly coke-making stage.
- Natural gas may substitute in some production processes for as much as 10% of coking coal (Eurofer 2019b).
 - Natural gas is a reducing agent in the production of Direct Reduced Iron (DRI) from iron ore, an alternative production route for crude steel.
 - This technology is not common in Europe (Pardo, Moya, and Vatopoulos 2015), with Ca.700 kt of DRI being produced in 2017 (Worldsteel 2018) - less than 1% of the EU total iron production, mainly due to high costs of gas.
- Along with other exploratory methods to enable the use of coals with lower quality in the coking process without undermining coke quality (e.g. stamp charging technology with oil additives, “Scope 21” coke-making process in Japan using high blending ratio (over 50%) of non- or slightly-coking coal) another substitute is the use of hypercoal as an additive to coking coal blend (Tercero et al. 2018) (Sundqvist Ökvist et al. 2018). The cost for hypercoal is higher, but it enables the use of some thermal coals (CRM experts 2019).
- Waste plastics in the coking coal blend can replace the use of 1-2% of coking coal (Tercero et al. 2018; SCRREEN / EC Data updates 2022). However, this negatively impacts coke quality, and it is possible to use only low amounts of secondary materials in the coking process (Sundqvist Ökvist et al. 2018).
- Hydrogen and natural gas potentially used in the blast furnace are not substitutes of coking coal *per se* as they do not provide mechanical support to the charge of the blast furnace nor the necessary carbon monoxide (CO) for reducing the iron ore but perform only the function of delivering heat (CRM experts 2019). However, in the future, specific processes may substitute coking coal with natural gas, hydrogen and biomass, e.g. Hisarna process (Pardo, Moya, and Vatopoulos 2015).

4 SUPPLY

EU SUPPLY CHAIN

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211

Figure 14 shows the coking coal flows (in C content) through the EU economy (data referred in year 2013).




Figure 14: Simplified MSA of coking coal flows in the EU, 2013 (BIO Intelligence Service 2015).

The annual average production of coking coal in EU during the period 2016-2020 was about 15 mt. Poland is the major producer with an average annual production 13 mt. Smaller amounts are extracted in Germany and Czech Republic. The extraction in Germany was interrupted after 2018. About 39 mt of coking coal were annually imported during 2016-2020. The most important trade partners are: United states (9.7 mt) Australia (5.6 mt) Canada (1.9) Russia (2.4). A small amount (3 mt) of coking coal, in comparison to produced + imported amount, was exported to third countries, mainly to: Ukraine, India, Serbia, Norway, South Africa and Turkey (Eurostat, 2021). Recycling is not applicable as coke is entirely dissipated after its use as it is oxidised to CO₂ (BIO Intelligence Service 2015). Therefore, the EOL-RIR is 0%.

In 2017, around 25% of the active hard coal mines in the EU produced metallurgical coal (and anthracite). In particular:

- In *Poland*, 18 hard coal mines were active in the Silesia (Śląskie) region, with 27% of coal produced in this region classified as coking coal;
- In *Czechia*, hard coal is mined at two underground mines located in the Moravskoslezsko region (Karviná and Darkov, ČSM), in which the extracted coal is graded as coking coal or steam coal based on its quality parameters. In the same region, the Paskov mine, with 89% of coal produced classified as coking coal, terminated its production in 2017;
- In *Germany*, two remaining underground hard coal mines produced steam coal and coking coal in 2016, the Prosper-Haniel mine, and the Ibbenbüren mine located in the Münster region (P. Alves Dias et al. 2018)(Euracoal 2017). Those mines were active only till the end of 2018. Therefore, Germany does not any longer contribute to the EU coking coal supply side.

This project has received funding from the European Union's Horizon 2020 research and innovation programme under grant agreement No 958211

In total, the share of coking coal in the overall EU hard coal production was on average 27% for the period 2016-2020 (WMD, since 1984). Despite domestic production, the EU remains dependent on imports of coking coal, with net import reliance of 72%. Due to the closure of mines in Germany, the EU import reliance was increased in comparison to the period 2012-2016 (import reliance 62%) (Eurostat, 2021).

In 2017, around 60 % of the EU crude steel production took place in integrated steelmaking plants (Blast furnace/Basic Oxygen furnace process), in which coke oven plants are typically an operational unit. Coking coal can also be converted into coke in individual coking plants before marketing to the iron industry. For example in Poland, the major producer of coking coal in the EU, coke is produced at the Przyjaźń and Zabrze coking plants operated by the mining company JSW (JSW 2019a).

SUPPLY FROM PRIMARY MATERIALS

GEOLOGY, RESOURCES AND RESERVES OF COKING COAL

GEOLOGICAL OCCURRENCE

Coal is a combustible, carbonaceous sedimentary rock, which is composed of fossilised plant remains, minerals and water. Coal is formed as accumulated dead plant materials in swamp ecosystems are buried beneath layers of younger sediments and altered by the combined effects of pressure and heat over millions of years to form individual carbon-rich coal layers, known as seams. The characteristics of coals are determined by the coalification process (e.g. varying types of buried vegetation, depths of burial, temperature and pressure at those depths, time of coal deposit formation). The composition and the amount of impurities (e.g. sulphur and phosphorous), the content of volatile matter and ash strongly condition the possible uses of the coal. For that reason, different groups and sub-groups of coal are identified, and each of them is used for specific purposes only. The most common classification of coals is based on rank, which represents the degree of coalification that has occurred. Classification of coals by rank ranges progressively from brown coals, which include lignite and sub-bituminous coal, to black or hard coals that comprise bituminous coal, semi-anthracite and anthracite. Anthracite (most carbonaceous) is classified as high-rank while lignite (least carbonaceous) is classified as low-rank. Coal types can be differentiated in the ranking sequence by several properties, e.g. elemental composition, volatile matter content, fixed carbon content, calorific value, water content, etc.; many different classification systems have been developed on a national and international level. Coking coal is classified as medium-rank bituminous coal which contains more carbon, less moisture and ash than low-rank coals. Coking coals usually have a volatile matter yield between 20% and 30% (dry, ash-free basis) (BGS 2010)(World Coal Association 2019)(World Coal Institute 2009)(Eurofer 2019b) (European Commission 2012).

The properties of coking coal have to be more tightly controlled than steam coal used in power stations and other uses, given the major impact of coke on blast furnace operation and pig iron composition. The required properties for coking coal to be suitable for steelmaking are low ash, sulphur and phosphorus content, as well as the ability to soften, swell and then solidify into a porous material of high strength when heated to a sufficiently high temperature in the absence of air (caking ability). A coal's caking properties are the primary

determinant of its suitability for coke production (BGS 2010)(World Coal Association 2019)(World Coal Institute 2009).

GLOBAL RESOURCES AND RESERVES:

Many different national and international definitions and classifications exist to subdivide coal resources into different classes, e.g. hard coal, brown coal, steam coal, coking coal, etc. These subdivisions are either based on scientific (physical, chemical, petrographic), technical (heating value, plasticity, swelling index), commercial, or combined parameters. As different definitions and cut-off values are used to subdivide the volumes of coal resources and reserves, e.g. into brown coal and hard coal, the resulting figures are not comparable (European Commission 2012). There are no resource and reserve data on coking coal at the national/regional level reported using the United Nations Framework Classification (UNFC)(European Commission 2017).

However, bituminous coal reserves can be a rough indication of raw materials suitable for extracting coking coal. The known reserves of anthracite and bituminous coal were approximately 718 billion tonnes at the end of 2017 (BP 2018), sufficient to meet the demand for centuries. The United States has the world’s largest reserves, followed by China and India (Table 8).

Table 8: Global proved reserves⁷⁶ of anthracite and bituminous coal at the end of 2017 (Data from (BP 2018))

Country	Bituminous coal and anthracite reserves (billion tonnes)	Percentage of the total (%)
US	220.8	30.7%
China	130.8	18.2%
India	92.8	12.9%
Russian Federation	69.6	9.7%
Australia	68.3	9.5%
Ukraine	32.0	4.5%
Kazakhstan	25.6	3.6%
Poland	19.8	2.8%
Indonesia	15.1	2.1%
South Africa	9.9	1.4%
Others	33.5	4.7%
Total world	718.3	100%

The United States holds the world’s biggest coal reserves. The nation’s proved coal reserves as of December 2018 stood at 250.2 billion tonnes (Bt) accounting for approximately 24% of the world’s proven coal reserves. The Russian Federation’s proven coal reserves as of December 2018 accounted for 15.2% of the world’s total. Australia’s proven coal reserves of 147.4Bt (2018 estimate) account for approximately 14% of the total proven coal reserves in the world. China’s proven coal reserves constitute 13% of the world’s total. More than 70% of China’s proved recoverable coal reserves are located in the north and north-west parts of the country. India’s proven coal reserves as of December 2018 accounted for more than 9% of the world’s total. Proven coal

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211

reserves of Indonesia as of December 2018 accounted for 3.5% of the world’s total proved coal reserves. Holding the biggest coal reserves in Europe, Germany hosts 3.4% of the world’s total proved coal reserves. Ukraine’s share in the world’s total proved coal reserves is 3.3%. Poland’s proven coal reserves at the end of 2018 accounted for approximately 2.5% of the world’s total proved coal reserves. With more than 400 coal deposits, Kazakhstan has approximately 2.4% of the world’s total proved coal reserves (mining-technology, 2021).

EU RESOURCES AND RESERVES

There are no published data on coking coal resources and reserves using the United Nations Framework Classification (UNFC). Reserves of 22 billion tonnes of anthracite and bituminous coal are reported in the EU, the majority of them is located in Poland (Table 9) mostly in the Upper Silesian basin (79% of the total hard coal reserves in Poland) where 27% of the hard coal reserves consists of coking coal (Eurocoal 2017). In Poland, the main producers of coking coal are the underground mines of Jastrzębska Spółka Węglowa S.A. (JSW). About 86% of the domestic production of this raw material comes from them (Kot-Niewiadomska, 2021). Other than the resource estimation reported in Minerals4EU website, deposit of antimony was reported in Rockliden, Sweden at 10 Mt with 0.18% Sb, (also contains 4.03% Zn, 1.82% Cu, 52 ppm Ag, 0.06 ppm Au) (Depaux, G., 2019).

Apart from Poland, coking coal is only exploited in the Czech Republic, and among European countries outside the EU—in Russia and Ukraine (WMD 2022). Its exploitation in Germany was completed in 2018. According to World Mining Data (WMD 2022), annual coking coal output in the EU has seen a steady decline from 25 million tonnes to 15 million tonnes between 2010 and 2018. In Poland, throughout the analysed period it remained at a similar level of about 12 million tonnes annually, constituting in recent years almost 80% of total output in the EU countries (Kot-Niewiadomska, 2021).

Table 9: EU total proved reserves⁷⁸ of anthracite and bituminous coal at the end of 2018 (Data from (BP 2019))

Country	Bituminous coal and anthracite reserves (billion tonnes)
Poland	20,542
Spain	868
Hungary	276
Bulgaria	192
Czechia	110
Romania	11
Germany	3
Total EU	22,002

Exploration and new mine development projects in the EU: In Poland, there are two ongoing new mine development projects in progress (Prairie Mining 2019):

- The *Jan Karski* project in the Lublin coal basin. The project has a potential to produce thermal and semi-soft coking coal. JORC-compliant total resources amount to 728 Mt of in-situ coal and probable ore reserves are estimated at 139.1 Mt of marketable coal, and the annual production can yield 6.3 Mt of marketable coal. The results of a pre-feasibility study were announced in March 2016.
- The *Debiensko* project in Upper Silesian coal basin. The project aims to produce premium hard coking coal (mid-vol and low-vol HCC). Resources reported under the JORC code comprise a total resource of 301 Mt of in-situ coal, and annual production is projected at 68 Mt of saleable coal over a 26 year period. A scoping study was published in March 2017.

PRODUCTION OF COKING COAL

Coal is mined by open-pit or underground methods, depending on the morphology of the coal deposit. Surface mining is applied when the coal seam is near the land surface (BGS 2010). Before marketing, Run-of-mine coal is upgraded in preparation plants where the extracted hard coal is graded as coking coal or steam coal, based on certain quality parameters. Preparation may include washing, crushing, sieving, and gravity concentration to satisfy size and purity specifications of the intended use.

The use of coking coal for metallurgical applications, i.e. steel production, require that certain physical and chemical properties are tested in advance in order to check the complete compatibility of the raw material with the production process (i.e. CSR index – coke strength after reaction). Moreover, also the content on impurities like sulphur and phosphorus, and not only, impose in which industrial processes the coking coal can be used. For this reason the coking coal is subdivided in different products: Premium Hard Coking Coal (PHCC), Hard Coking Coal (HCC), High-Volatile HCC (Semi-HCC), Semi-soft coking coal (SSCC), Low Vol PCI, each of them identified by different properties and performance when employed in the industrial processes. In general, the EU steel production should be fed using Premium HCC and HCC for maintaining the high environmental performance of the installations (i.e. higher quality HCC means the use of less raw materials and lower emissions). In particular, the European integrated steel process routes uses the most advanced technologies using PHCC and HCC only, in compliance with European environmental laws. Any substantial substitution of these high-quality coking coals will surely increase the whole environmental impact (Eurofer 2019b).




Figure 15: Coking coal products (European Commission 2014)

WORLD AND EU MINE PRODUCTION OF COKING COAL




Figure 16: Global coking coal production since 1984 according to WMD (WMD, since, 1984)

The global production of coking coal decreased by 3.2% in 2020. Contrary to the others producers, China increased production by 2.8%, up by 15 Mt. On the other side of the Pacific, production in the United States decreased by the same tonnage, -15 Mt, representing a cut of 23%. Production in Australia and the Russian

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211

Federation also decreased, by -2.8% and -6.8% respectively (iea.org, 2022). Figure 16 presents the global production of coking coal according to WMD data. As it can be seen, China and Australia consists the major producers, with 553 and 184 Mt respectively, in 2020 (WMD, since 1984). A notable coking coal production is taking place also in Russia, United States and India, with 88.2, 50.4 and 44.8 Mt, respectively.

OUTLOOK FOR SUPPLY

The demand for raw steel is a key indicator for coking coal production and consumption. About 70 per cent of iron is manufactured using blast furnace technology, which requires metallurgical coal. Steel demand is driven by the economic and population growth in countries such as China and India. Macroeconomic data show that steel demand is going to increase until 2030 (eia.gov, 2022). Nevertheless, the coking coal demand and production is expected to be decreased until 2030 in the Asia-Pacific Economic Cooperation region. APEC region comprises all the major coking coal producers apart of India. The coking coal limitation will be based on: (a) the intensification of steel scrap recycling, the (b) exploitation of high-quality coal deposits in Australia which are going to reduce steel industry carbon emissions (minerals.org.au, 2022), and (c) the application of modern technologies in the industry (i.e. involving of hydrogen in the production process) (coal.jogmec, 2022).

In the APEC region, metallurgical coal production is projected to decline from 25 exajoules in 2019 to 22 EJ in 2030, led by declines in the US (-34%), Canada (-18%) and China (-13%). Australia and Russia are projected to post a small reduction in metallurgical coal production to 2030 (Figure 17). According to the Institute for Energy Economics and Financial Analysis (IEEFA), there was a 35% decline in metallurgical coal output from mines in the Appalachian region of the U.S in 2020 (IEEFA, 2020). This pandemic impact has brought forward some of the declines that were anticipated to occur out to 2030. Almost all of China’s metallurgical coal production is used by its domestic steel industry. The projected decreasing trend out to 2030 is driven by a softening steel production outlook over the medium- to longer-term (aperc.or.jp, 2021).




Figure 17: Coking coal production (expressed in petajoules) since 2000 and production forecast until 2030 in APEC region (aperc.or.jp, 2021).

SECONDARY PRODUCTION

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211

There is no secondary production of coking coal

PROCESSING OF COKING COAL

Coking coal is converted into coke, semi-coke and coke by-products in coke ovens. Coke making, or carbonisation, entails heating the coal to high temperatures (1,150 to 1,350°C) in the absence of oxygen to drive off gases and impurities and concentrate the carbon content (Remus et al. 2013). Semi-coke is formed by incomplete carbonisation of coal, with a reduced air supply, at a temperature of between 450 and 700°C.

Before coke making, selected bituminous coal grades are usually blended and pulverised to control the size and quality of the feed. During heating, the physical properties of coking coal allow the coal particles to pass through softening, fusing, and solidification into hard and porous coke lumps. They are then quenched with either water or air before storage or direct transfer to the blast furnace. Exhaust gases are collected and processed to recover combustible gases for heat production and other by-products (Remus et al. 2013)(Diez, Alvarez, and Barriocanal 2002). The coke yield varies from 700 kg to 800 kg of dry coke per tonne dry coal (approximately 1250-1400 kg coking coal is needed for the production of 1 tonne of coke depending on the volatile content), and the coke oven gas production ranges from 140 kg to 200 kg per tonne dry coal. The yield of tar and benzole (benzene, toluene, and xylene) is reported to be 50 kg per tonne dry coal (ICHPW 2019) The industrial methodology of coke production in summarized in the flowsheet of Figure 18.




Figure 18: Flowsheet of the processing of coking coal for coke production (epa.gov, 1995).

This project has received funding from the European Union's Horizon 2020 research and innovation programme under grant agreement No 958211

OTHER CONSIDERATIONS

HEALTH AND SAFETY ISSUES RELATED TO THE COKING COAL OR SPECIFIC/RELEVANT COMPOUNDS AT ANY STAGE OF THE LIFE CYCLE

Coking coal is produced in coke ovens, and the coking coal is used in the aluminium, steel, graphite, electrical, and construction industries. Chronic (long-term) exposure to emissions from coke ovens and from the aforementioned industries results in conjunctivitis, severe dermatitis, lesions of the respiratory system and digestive system. Epidemiologic studies of coke oven workers have reported an increase in cancer of the lung, trachea, bronchus, kidney, prostate, and other sites. Animal studies have reported tumours of the lung and skin from inhalation exposure to coal tar. EPA (Environmental Protection Agency) has classified coke oven emissions as a Group A, known human carcinogen. (IRIS 2022).

(OSHA 2022) define several permissible exposure levels. Due to the carcinogenic properties, the exposition to coking oven emissions shall be reduced to lowest feasible concentrations (OSHA 2022). Occupational exposition limits for dusts and volatile substance emissions from coal are defined in the EU and other countries. (GESTIS 2022)

Emissions from coke oven processes into the environment are regulated in the Industrial Emissions Directive (IED 2010) in the EU.

ENVIRONMENTAL ISSUES

Production and use of coking coal cause a considerable share of the world's carbon dioxide emissions. The steel industry alone is responsible for around 5 % of CO₂ emissions in the EU, 22 % of industrial emissions excluding combustion, and 7 % globally. Most of the emissions come from the iron ore reduction process, in which the carbon provided by the coke acts as the reductant. Reducing the carbon intensity of the blast furnace steelmaking route is, therefore, one of the two methods - the other is the increased share of the electric furnace steelmaking route - to decarbonise the steel industry. Among the novel technologies to achieve emissions reduction are carbon capture and storage, carbon capture and utilisation, hydrogen-based steelmaking, iron ore electrolysis. Such breakthrough innovations will constitute an entirely new production system that would replace production processes that have been used and optimised for many decades. As an example, the hydrogen-based direct reduction process aims using hydrogen to completely bypass the use of coal for the production of primary steel (European Commission 2018). However, they are not going to be available in the next decade. (IChPW 2019, JRC 2022).

NORMATIVE REQUIREMENTS RELATED TO MINING, USE AND PROCESSING OF THE COKING COAL

Coking coal is produced from coal. The US-EPA published "Coal Mining Effluent Guidelines" covering wastewater discharges from mine drainage, coal storage facilities, and coal preparation plants. (Coal Mining

Guidelines 2002).⁶ The 2013 Bettercoal Code is an international standard for assessing, assuring and sustaining ethical, environmental and social performance across the coal mining supply chain. (Bettercoal 2013)

The above guidelines are exemplary for other guidelines and standards that can be found related to coal mining and processing.

SOCIO-ECONOMIC AND ETHICAL ISSUES

ECONOMIC IMPORTANCE OF COKING COAL FOR EXPORTING COUNTRIES

Table 10 lists the countries for which the economic value of exports of coking coal represents more than 0.1 % in the total value of their exports.

Table 10: Economic share of Coking coal exports in total exports

Country	Export value (USD)	Share in total exports (%)
Mongolia	7576310834	27.62%
Colombia	3,1056E+10	13.41%
Australia	2,4505E+11	12.28%
South Africa	8,5227E+10	4.52%
Russian Federation	3,37104E+11	3.33%
Indonesia	1,6319E+11	2.36%
Bosnia Herzegovina	6152512537	1.50%
Mozambique	3460032908	1.00%
Zimbabwe	4394837096	0.97%
Canada	3,8838E+11	0.88%
Poland	2,5417E+11	0.69%
USA	1,4303E+12	0.43%
Kazakhstan	4,6949E+10	0.34%
Belarus	2,9179E+10	0.22%
Botswana	4255975840	0.16%
Czechia	1,9231E+11	0.10%
Japan	6,4128E+11	0.10%

Source: COMTRADE (2022), based on data for 2020

For Mongolia (27.62%), Colombia (13.41%) and Australia (12.28%) the value of coking coal exports represent a share of their exports, with a percentage above 10%. For South Africa (4.52 %), Russian Federation (3.33 %), Indonesia (2.36 %), Bosnia (1.50 %), Mozambique (1.00 %) the value of coking coal exports represents more than 1% of the total value of their exports. Zimbabwe (0.97 %), Canada (0.88 %), Poland (0.69 %), USA (0.43 %), Kazakhstan (0.34 %), Belarus (0.22 %), Botswana (0.16 %), Czechia (0.10 %), Japan (0.10 %) export coking coal, whose value still accounts for more than 0.1 % of their total exports. For all other exporting countries, this share is below 0.1 %.

⁶ Even though the source is from 2002, the document is still integrated into the US-EPA's National Pollutant Discharge Elimination System (NPDES, <https://www.epa.gov/npdes>) and is thus still considered an applicable normative requirement.

This project has received funding from the European Union's Horizon 2020 research and innovation programme under grant agreement No 958211

SOCIAL AND ETHICAL ASPECTS

Coking coal faces political, technical and financial challenges in the transition to a lower-carbon economy (CRM Alliance 2018). The decline in coal-related activities might also affect the iron and steel sector. Hard coal mines capable of producing this type of coal could continue to operate purely by serving this sector, as long as coking coal prices are sufficient enough to sustain mining operations (P. Alves Dias et al. 2018).

For the EU, social aspects of coal mining and processing are related to the transition to a low-carbon/carbon-free society. The EU coal sector currently employs nearly half million people in direct and indirect activities. By 2030, it is estimated that around 160 000 direct jobs may be lost. Regional development based on a carefully planned restructuring process, to which renewable energy plays central role, will create new employment opportunities (Alves Dias et al. 2018).

Outside the EU, human rights violations in the context of coal mining are of relevance. The most important human rights Risk Areas in mining generally revolve around certain major fields, such as “Indigenous,” “Land”, “Environment”, “Labor”, “Conflict” and “Corruption” (BGR 2016).

RESEARCH AND DEVELOPMENT TRENDS

RESEARCH AND DEVELOPMENT TRENDS FOR LOW-CARBON AND GREEN TECHNOLOGIES

- INSTABRIQ⁷: Briquetting machine for coal dust recycling (2018 – 2019)

Coke is a low-sulfur fuel used in the production of steel by steelworks. During this process, up to 0.5 kg of coke dust per tonne is cast off. Coke dust is harmful to human health and the environment as it contains metal contaminants. Contaminant-free coke dust can turn into coke briquettes with the use of binding agents and adhesives. However, they release environmentally harmful SO₂ and NO_x gases. Reducing sulfur and nitrogen in coal can significantly restrict the percentage of CO₂ released into the environment. The INSTABRIQ project proposes a new type of briquetting machine that creates low-sulfur ‘clean coal’ briquettes. The technology can compress any coal dust without the use of adhesives, increasing the amount of recycled coal.

OTHER RESEARCH AND DEVELOPMENT TRENDS

- Mechanism of destruction of caking property of a coking coal using low-temperature pyrolysis treatment, Wang et al. 2022⁸

A low-temperature pyrolysis treatment (LTPT) to destroy the caking property of a coking coal is proposed. Physicochemical properties of the coal before and after LTPT were investigated using Fourier transform infrared spectroscopy, thermogravimetric analysis, automatic microscope photometry, and gas chromatography with mass spectrometric detection. Hot-stage microscopy was used to show in-situ morphological changes in metaplast formation during the LTPT. The results showed that the caking index (G)

⁷ <https://cordis.europa.eu/project/id/832339>

⁸ <https://www.sciencedirect.com/science/article/abs/pii/S0165237022003345>

This project has received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement No 958211

of the coking coal decreased with an increase in temperature, reaching zero at 468 °C. The lower the vitrinite content, the lower was the G value of the treated sample.

REFERENCES

Alves Dias, P. et al. (2018), EU coal regions : opportunities and challenges ahead. JRC Science for Policy Report. Joint Research Center (JRC). European Commission (EC). doi: 10.2760/064809.

aperc.or.jp (2021), APERC Coal Report, Asia Pacific Energy Research Centre, available at: https://aperc.or.jp/file/2022/2/3/2021+Coal_Report.pdf, accessed in: 06-02-2023.

BGS (2010), 'Mineral Profile: Coal'. Available at: <https://www.bgs.ac.uk/mineralsUK/statistics/mineralProfiles.html>.

BIO Intelligence Service (2015), Study on Data for a Raw Material System Analysis: Roadmap and Test of the Fully Operational MSA for Raw Materials. Available at: <https://ec.europa.eu/jrc/en/scientific-tool/msa>.

BP (2018), Statistical Review of World Energy. 67th edition. Available at: <https://www.bp.com/content/dam/bp/business-sites/en/global/corporate/pdfs/energy-economics/statistical-review/bp-stats-review-2018-full-report.pdf> (Accessed: 3 July 2019).

BP (2019), Statistical Review of World Energy - all data, 1965-2018. Available at: <https://www.bp.com/en/global/corporate/energy-economics/statistical-review-of-world-energy.html> (Accessed: 5 July 2019).

BP (2022), Statistical Review of the World 2022, <https://www.bp.com/en/global/corporate/energy-economics/statistical-review-of-world-energy.html>, accessed on October 2022

coal.jogmec(2022), Trends and challenges in the European coking coal market, available at: <https://coal.jogmec.go.jp/content/300376752.pdf>, accessed in: 06-02-2023.

Diez, M. A., Alvarez, R. and Barriocanal, C. (2002), 'Coal for metallurgical coke production : predictions of coke quality and future requirements for cokemaking', *International Journal of Coal Geology*, 50, pp. 389–412. Available at: <https://www.sciencedirect.com/science/article/pii/S0166516202001234>.

eia.gov (2022), Short-Term Energy Outlook Coal Module, available at: https://www.eia.gov/analysis/handbook/pdf/STEO_Coal_Model.pdf, accessed in: 06-02-2023.

epa.gov (1995), Coke Production, available at: https://gaftp.epa.gov/ap42/ch12/s02/final/c12s02_1995.pdf, accessed in: 06-02-2023.

Euracoal (2017), Coal Industry Across Europe. 6th edition. Available at: <https://euracoal.eu/library/publications/>.

Euracoal (2018), 'Market Report 1/2018', (April 2018). Available at: <https://euracoal.eu/library/coal-market-reports/>.

Euracoal (2019), International coal trade. Available at: <https://euracoal.eu/coal/international-coal-trade/> (Accessed: 9 July 2019).

Eurocoal (2021), EURACOAL Market Report 2021 no.1, <https://euracoal.eu/library/coal-market-reports/>, accessed on October 2022

- European Commission (2011), Critical raw materials. Available at: https://ec.europa.eu/growth/sectors/raw-materials/specific-interest/critical_en (Accessed: 8 July 2019).
- European Commission (2012), 'European Coal resources : a geographical database and map of EU coal basins including potential sources of coal bed methane based on a harmonised typology Terminology and classification for the EUCORES', p. 31. Available at: <http://ec.europa.eu/energy/coal/eucores/doc/20120805-eucores-proposal-classification.pdf>.
- European Commission (2014) Report on critical raw materials for the EU - Critical raw materials profiles. Available at: <https://ec.europa.eu/docsroom/documents/11911/attachments/1/translations/en/renditions/pdf>.
- European Commission (2017), Study on the review of the list of critical raw materials. Non-Critical Raw Materials Factsheets. European Commission. doi: 10.2873/876644.
- European Commission (2018), In-depth analysis in support of the Commission Communication COM(2018)/773. 'A Clean Planet for all. A European strategic long-term vision for a prosperous, modern, competitive and climate neutral economy'. Available at: https://ec.europa.eu/clima/sites/clima/files/docs/pages/com_2018_733_analysis_in_support_en_0.pdf.
- European Commission (2019) Negotiations and agreements - Trade. Available at: <http://ec.europa.eu/trade/policy/countries-and-regions/negotiations-and-agreements/> (Accessed: 7 July 2019).
- European Commission (2020), Study on the EU's list of Critical Raw Materials, <https://doi.org/10.2873/904613>, accessed on October 2022
- Eurostat Comext (2022), Eurostat database. EU trade since 1988 by HS2-4-6 and CN8 (DS-045409). , <http://epp.eurostat.ec.europa.eu/newxtweb/> , accessed on October 2022
- Eurostat (2021), Comext International Trade [Online]. Available at: <http://epp.eurostat.ec.europa.eu/newxtweb/mainxtnet.do>
- Georgitzikis, K., D'elia, E. and Eynard, U. (2022), Titanium metal: Impact assessment for supply security, European Commission, 2022, JRC129594. , -, accessed on October 2022
- IChPW (2019), 'Institute for Chemical Processing of Coal. Expert comments'.
- IEA (2021), Coal 2021: Analysis and forecast to 2024, <https://www.iea.org/reports/coal-2021>, accessed on October 2022
- iea.org(2022), Coal Information: Overview. Available at: <https://www.iea.org/reports/coal-information-overview/production>, accessed in: 06-02-2023.
- IEEFA (2020), Institute for Energy Economics and Financial Analysis. <https://ieefa.org/eia-2020-u-s-coal-production-to-total-530-million-tons-down-25-from-prior-year/> (accessed September 15(2021),
- JSW (2019a), Coke and By-Products, Jastrzębska Spółka Węglowa SA - For contractors -. Available at: <https://www.jsw.pl/en/for-contractors/coke-and-by-products/> (Accessed: 12 July 2019).
- JSW (2019b), 'Revision of Critical Raw Materials list. JSW SA position paper'.
- Kot-Niewiadomska, A., Galos, K., Kamyk, J. (2021), Safeguarding of Key Minerals Deposits as a Basis of Sustainable Development of Polish Economy. Resources, 10, 48.

This project has received funding from the European Union's Horizon 2020 research and innovation programme under grant agreement No 958211

Li, A. (2021), INFOGRAPHIC: Global coking coal imports hit by Covid-19, <https://www.fastmarkets.com/insights/infographic-global-coking-coal-imports-hit-by-covid-19>, accessed on October 2022

minerals.org.au(2022), COMMODITY DEMAND Outlook 2030, MINERALS COUNCIL OF AUSTRALIA & COMMODITY INSIGHTS, available at: <https://www.minerals.org.au/sites/default/files/Commodity%20Outlook%202030.pdf>, accessed in: 06-02-2023.

mining-technology (2021), Countries with the biggest coal reserves. Available at: <https://www.mining-technology.com/features/feature-the-worlds-biggest-coal-reserves-by-country/>, accessed in: 06-02-2023.

Prairie Mining (2019), Prairie Mining Limited. Projects. Available at: <http://www.pdz.com.au/> (Accessed: 8 November 2019).

SCRREEN 2 experts (2022), Material Validation sessions

SCRREEN2 / EC Data (2022), EC Data assessment data (Coking Coal 2023)

VDKI (2017), Annual Report 2017. Facts and Trends 2016/2017. Verein der Kohlenimporteure. Available at: <https://english.kohlenimporteure.de/publications/annual-report-2018.html>.

VDKI (2022), Annual report 2021. Facts and Trends 2020/21. Verein der Kohlenimporteure.

WMD (2022), Federal Ministry of Agriculture, Regions and Tourism of Austria (Ed.): World Mining Data (since 1986).

World Coal Association (2019), How is steel produced?, What is coal. Available at: <https://www.worldcoal.org/coal> (Accessed: 3 July 2019).

World Coal Institute (2009), Coal & Steel report. Available at: papers3://publication/uuid/3F82BBD9-61F6-4283-8B55-43FAC4DFB0F5.